



TEST REPORT

Test Report # 19W-011062 Date of Report Issue: July 22, 2019
Date of Sample Received: July 19, 2019 Pages: Page 1 of 6

CLIENT INFORMATION:

Company: Xiamen Boshun Cutlery Co.Ltd
Address: No. 256 Tongan Park,
Tongan Industrial Centralized Area
Xiamen City China 361100



SAMPLE INFORMATION:

Product Name: stainless steel spoon
Product Reference No.: spoon St Hubert
Style No.: -
Order No.(PO No.): 10STHUB112333
Country of Origin: China
Country of Distribution: Europe
Testing Period: 07/22/2019-07/22/2019

OVERALL RESULT:

PASS

Please refer to the following pages for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION
TESTING TECHNOLOGY CO., LTD

Kevin Lee
Technical Manager



HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158
5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainspection Testing Technology Co., Ltd



TEST REPORT

Test Report # 19W-011062 Date of Report Issue: July 22, 2019
Date of Sample Received: July 19, 2019 Pages: Page 2 of 6

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	Regulation (EC) No 1935/2004-Sensorial examination odour and taste test
PASS	Regulation (EC) No 1935/2004 and Council of Europe Resolution CM Res(2013)9 on metals and alloys used in food contact materials and articles - Specific release of heavy metals

Remark: Test results are transferred from test report no. 19W-010349 date: 07/18/2019



HANGZHOU ASIAINPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158
5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainpection Testing Technology Co., Ltd

**DETAILED RESULTS:****Regulation (EC) No 1935/2004-Sensorial examination odour and taste test**

Test Method:DIN 10955: 2004

Test condition: 70°C, 2 hours

Test media:Distilled water

No. of panelist: 6

Specimen No.	2	---	---	---	Max.Permissible Limit
Test Item	Result	Result	Result	Result	
Sensorial examination odour (Point scale)	0	---	---	---	2.5
Sensorial examination taste (Point scale)	0	---	---	---	2.5
Conclusion	PASS	---	---	---	

Scale evaluation:

0: No perceptible odour

1: Odour just perceptible (still difficult to define)

2: Moderate odour

3: Moderately strong odour

4: Strong odour



**DETAILED RESULTS:****Regulation (EC) No 1935/2004 and Council of Europe Resolution CM Res(2013)9 on metals and alloys used in food contact materials and articles - Specific release of heavy metals**

Test method: Sample preparation in 0.5%(5g/L) citric acid at 70°C for 2 hours, ISO 17294-2:2016

Analytical Method: Inductively Coupled Plasma-Mass Spectrometry

Specimen No:	1					
Test Item(s)	Unit	MDL	1 st + 2 nd Migration		3 rd Migration	
			Result	7xSRL ^{*2}	Result	SRL ^{*1}
Aluminum (Al)	mg/kg	0.5	ND	35	ND	5
Antimony (Sb)	mg/kg	0.01	ND	0.28	ND	0.04
Chromium (Cr)	mg/kg	0.1	ND	1.75	ND	0.25
Cobalt (Co)	mg/kg	0.01	ND	0.14	ND	0.02
Copper (Cu)	mg/kg	0.5	ND	28	ND	4
Iron (Fe)	mg/kg	5	ND	280	ND	40
Magnesium(Mg)	mg/kg	0.1	ND	---	ND	---
Manganese (Mn)	mg/kg	0.5	ND	12.6	ND	1.8
Molybdenum (Mo)	mg/kg	0.05	ND	0.84	ND	0.12
Nickel (Ni)	mg/kg	0.05	ND	0.98	ND	0.14
Silver (Ag)	mg/kg	0.05	ND	0.56	ND	0.08
Tin ^{*3} (Sn)	mg/kg	5	ND	700	ND	100
Titanium(Ti)	mg/kg	0.1	ND	---	ND	---
Vanadium (V)	mg/kg	0.005	ND	0.07	ND	0.01
Zinc (Zn)	mg/kg	0.5	ND	35	ND	5
Arsenic (As)	mg/kg	0.001	ND	0.014	ND	0.002
Barium (Ba)	mg/kg	0.1	ND	8.4	ND	1.2
Beryllium (Be)	mg/kg	0.005	ND	0.07	ND	0.01
Cadmium (Cd)	mg/kg	0.001	ND	0.035	ND	0.005
Lead (Pb)	mg/kg	0.005	ND	0.07	ND	0.01
Lithium (Li)	mg/kg	0.005	ND	0.336	ND	0.048
Mercury (Hg)	mg/kg	0.0005	ND	0.021	ND	0.003
Thallium (Tl)	mg/kg	0.00005	ND	0.0007	ND	0.0001
Conclusion	PASS					

Note:

(1) mg/kg =milligram per kilogram

(2) SRL = Specific Release Limit

(3) *1 Compliance is established on the result from the third migration test for repeated used articles.

(4) *2 Meantime, the sum of the results of the first and second tests should not exceed 7 times the SRL

(5) *3 Except in field of application under Regulation (EC) No.1881/2006.(canned food container)

HANGZHOU ASIANSPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158
5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainspection Testing Technology Co., Ltd

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Silvery metal	Main body
2	Stainless steel spoon	Finished product





SAMPLE PHOTO:



-End Report-

